Temperature effects in the band structure of topological insulators

Bartomeu Monserrat^{1, 2, *} and David Vanderbilt¹

¹Department of Physics and Astronomy, Rutgers University, Piscataway, New Jersey 08854-8019, USA

²TCM Group, Cavendish Laboratory, University of Cambridge,

J. J. Thomson Avenue, Cambridge CB3 0HE, United Kingdom

(Dated: August 3, 2016)

We study the effects of temperature on the band structure of the Bi_2Se_3 family of topological insulators using first-principles methods. Increasing temperature drives these materials towards the normal state, with similar contributions from thermal expansion and from electron-phonon coupling. The band gap changes with temperature reach 0.3 eV at 600 K, of similar size to the changes caused by electron correlation. Our results suggest that temperature-induced topological phase transitions should be observable near critical points of other external parameters.

Topological insulators and related materials have consolidated as a new field of condensed matter of both fundamental and applied interest. Potentially novel applications have motivated the search for new materials exhibiting topological properties. In this quest, composition [1], pressure [2, 3], strain [4, 5], and electromagnetic fields [6–8] have all been used to control topological order. By contrast, temperature has so far exclusively played a passive role, for example constraining the quantum anomalous Hall effect to the milikelvin regime [9], and thus limiting potential applications of the associated dissipationless currents. Only recently have Saha and coworkers proposed that temperature can also be exploited when studying topological materials, for example by using phonon linewidths to identify band inversions [10].

The effects of temperature on topological insulators can be divided into two areas. The first concerns the electronic occupation of states, leading to questions such as the proper definition of topological invariants, which must then be based on the density matrix rather than the ground state wave function [11–14]. The second relates to the renormalization of the single-particle bands, which could lead to temperature-induced band inversions [15, 16], and it has been argued on the basis of simple models that temperature should favor topological phases.

First-principles calculations have proved central in predicting new topological materials and their behaviour, many times leading to subsequent experimental observation [17, 18]. The study of temperature effects on topological materials would equally benefit from firstprinciples calculations, but none have been available. Fully first-principles calculations of the temperature dependence of band structures have only recently become possible, as first and second order terms in the electronphonon interaction contribute similarly and must be included on an equal footing [19, 20]. Because of such difficulties, to date these calculations have only been performed on simple semiconductors and insulators [21–25].

In this work, we study the effects of temperature on topological insulators with first-principles methods. Using the Bi_2Se_3 family of topological insulators, we demonstrate the feasibility of such calculations and unravel the

importance of temperature when studying topological order. Our calculations show that both thermal expansion and electron-phonon coupling make similar contributions to the temperature dependence of band structures, and that, at variance with predictions from model studies [15, 16], increased temperature tends to suppress topological order in these materials.

We consider the Bi₂Se₃ family of compounds for our first-principles study [17]. Bi₂Te₃, Bi₂Se₃, and Sb₂Te₃ crystallize in the rhombohedral $R\overline{3}m$ space group, with five atoms in the primitive cell. They form a layered structure, in which groups of five layers are tightly bound (so-called quintuple layers), and these are then weakly bound to each other. Sb₂Se₃ has *Pnma* symmetry in its ground state. Metastable structures of these compounds have been synthesized [26], and in particular the $R\overline{3}m$ structure of Sb₂Se₃ has been experimentally studied [3]. In this work, we consider the $R\overline{3}m$ structure for all compounds.

Our calculations are based on density functional theory (DFT) using the VASP package [27–30]. We use the PBE functional [31] and the projector augmented-wave method [32, 33] with an energy cut-off of 600 eV and a **k**-point grid of size $12 \times 12 \times 12$ for the primitive cells and commensurate grids for the supercells. All calculations are performed with spin-orbit coupling unless otherwise stated.

The PBE functional overestimates static volumes and thermal expansion compared to experiment. For example, in Bi₂Se₃ the experimental hexagonal c axis at 10 K is 28.48 Å [34], compared with the PBE c axis of 30.21 Å. Therefore, we use experimental volumes when available. For Bi₂Se₃ and Sb₂Te₃, experimental data is only available up to about 250 K [34], and we fit a Bose factor to this data to extrapolate to higher temperatures, which is justified in this case as the linear asymptotic regime is already reached at the highest temperatures for which data is available [35]. For Bi₂Te₃, data is available up to 600 K [36]. No data is available for the rhombohedral structure of Sb₂Se₃, so in this case we use the structure relaxed using the PBE functional. The atomic coordinates of all atoms are relaxed until the forces are smaller than 10^{-3} eV/Å .

The phonon and electron-phonon coupling calculations are performed using the finite displacement method in conjunction with the recently developed nondiagonal supercell approach [37]. Finite displacement methods allow us to straight-forwardly incorporate the effects of the spin-orbit interaction on electron-phonon coupling which, as far as we are aware, has never been attempted in this context. The reported results correspond to a vibrational Brillouin zone sampling using grid sizes of $4 \times 4 \times 4$, as calculations for Bi₂Se₃ using grids of size $8 \times 8 \times 8$ show that the electron-phonon induced band gap corrections are converged to better than 8 meV at all temperatures considered. The matrix of force constants is constructed by considering small positive and negative symmetry-inequivalent atomic displacements of amplitude 0.005 Å. The dynamical matrix, obtained by a Fourier transformation, is diagonalized to calculate the vibrational frequencies $\omega_{\mathbf{q}\nu}$ at each phonon wave vector **q** and branch ν . The band gap at temperature T is then calculated as [19-25]

$$E_{\rm g}(T) = E_{\rm g}^{\rm static} + \frac{1}{N_{\mathbf{q}}} \sum_{\mathbf{q},\nu} \frac{a_{\mathbf{q}\nu}}{\omega_{\mathbf{q}\nu}} \left[\frac{1}{2} + n_{\rm B}(\omega_{\mathbf{q}\nu},T) \right], \quad (1)$$

where $a_{\mathbf{q}\nu}$ are the electron-phonon matrix elements averaged over $N_{\mathbf{q}}$ **q**-points, and $n_{\rm B}$ is a Bose-Einstein factor. The electron-phonon matrix elements are determined using finite displacements along the normal modes of vibration.

The topological nature of the Bi₂Se₃ family of compounds is determined by the parity of the occupied bands at the Γ point, where band inversion occurs in the presence of spin-orbit coupling [17]. Therefore, in order to investigate the effects of temperature on the topological order, we focus on the temperature dependence of the band gap at Γ , as shown in Fig. 1.

Bi₂Te₃, Bi₂Se₃, and Sb₂Te₃ are topological insulators, and their gaps close with increasing temperature. Using Bi_2Se_3 as an example, we observe that the gap closure is driven by both thermal expansion and electron-phonon coupling. Thermal expansion alone (orange dashed line) closes the band gap by almost 0.1 eV at 600 K. Electronphonon coupling alone (blue dashed-dotted line) causes a change in the band gap of 0.1 eV at 600 K. The asymptotic linear dependence of the gap change with temperature is reached at around 100 K, determined by the lowenergy vibrations that are a consequence of the heavy atoms in the compounds under study. Thermal expansion and electron-phonon coupling make similar contributions, and therefore both must be included (red solid line). To date, the vast majority of first-principles calculations of the temperature dependence of the band gap have neglected the effects of thermal expansion. This may be justifiable for simple materials made of light atoms, such as diamond and silicon, that exhibit weak



FIG. 1. Temperature dependence of the Γ -point band gaps of the Bi₂Se₃ family of compounds. The black dotted lines correspond to the static lattice band gaps; the orange dashed and blue dashed-dotted lines show the result of including only thermal expansion or only electron-phonon coupling effects, respectively; and the red solid curves give the total temperature dependence.

thermal expansion. By contrast, topological insulators are composed of heavy elements, for which thermal expansion is important as shown in Fig. 1.

Not surprisingly, for Sb₂Se₃, which is already a normal insulator with an uninverted gap at low temperature, the same electron-phonon effects lead instead to a band gap opening with increasing temperature. Thermal expansion also tends to increase the band gap, but we have not included this contribution as there is no experimental data available for this system.

The sizes of the band gap shifts are similar to those observed and calculated in many semiconductors and insulators. The only reported phonon-induced gap shifts in topological insulators we are aware of are those of Kim and Jhi, who theoretically studied the change in the band gap induced by exciting selected phonon modes in a series of IV-VI semiconductors and found shifts on the 0.1 eV scale [38]. In the Bi₂Se₃ family of compounds, zero-point contributions are small, in the range 0.01-0.02 eV in all systems, but thermal changes are larger, reaching 0.2-0.3 eV at 600 K. The GW approximation has been shown to correct the DFT gaps by about 0.2-0.3 eV in the Bi₂Se₃ family of compounds [39], to lead to qualitative changes in the shape of the bands near Γ [40], and more generally to question the validity of some predictions of topological insulators based on semilocal DFT [41]. Our results show that the effects of temperature modify the band structure to a similar extent, and therefore should also be included



FIG. 2. Phonon dispersion of Bi_2Se_3 with mode resolved electron-phonon coupling strength without (left) and with (right) spin-orbit coupling. The area of the circles are proportional to the strength of electron-phonon coupling, and the sign of the coupling is positive (gap opening) for blue circles and negative (gap closing) for red circles.

for an accurate description of topological insulators.

We next investigate the microscopic origin of the electron-phonon coupling strength, taking Bi₂Se₃ as an example. In Fig. 2 we show the phonon dispersion of Bi_2Se_3 along the high-symmetry line from Γ at \mathbf{q} = (0,0,0) to T at $\mathbf{q} = (0.5, 0.5, 0.5)$, chosen because electron-phonon coupling is strongest along this line. The mode-resolved strength of electron-phonon coupling to the direct band gap at the electronic Γ point is indicated by the filled circles, and shown both without and with spin-orbit coupling. The inclusion of the spin-orbit interaction has two effects. The first is to reverse the gap-opening induced by electron-phonon coupling to gap closing upon band inversion. The second is to modify the strength of electron-phonon coupling beyond the mere exchange of band extrema. For example, the gap closing induced by the modes at $\mathbf{q} = (0.25, 0.25, 0.25)$ with spin-orbit coupling is larger than the opening of the gap induced by the same modes when spin-orbit coupling is not included. For Bi_2Te_3 and Sb_2Te_3 , similar behaviour is observed, but for Sb_2Se_3 , the inclusion of spin-orbit coupling does not induce a band inversion, and therefore the sign of the band gap correction does not reverse.

A detailed analysis of the couplings reveals that the modes that couple most strongly to the electronic states are those that involve atomic vibrations along the *c*-axis that change the interlayer distance. It is also the change in length of the *c*-axis that drives the band gap change due to thermal expansion. This can be explained by the nature of the states at the band extrema of the Γ point,



FIG. 3. Pressure-temperature phase diagram of Sb₂Se₃.

which mainly arise from the hybridized p orbitals of the constituent atoms. The crystal field splits the p_z from the $p_{x,y}$ orbitals, which remain degenerate, and it is the p_z that form the band extrema and undergo band inversion when the spin-orbit interaction is included [17]. Changing the interlayer distance, either by atomic vibrations or by lattice expansion, modifies the states at the gap edges, and thus drives the observed temperature dependence.

The inclusion of temperature in our calculations allows us to construct the pressure-temperature phase diagram of Sb₂Se₃ shown in Fig. 3. Sb₂Se₃ is a normal insulator under ambient pressure, but with increasing external pressure it undergoes a phase transition to a topological insulator at 2.5 GPa [3]. First-principles calculations based on the PBE functional give a transition pressure of 1.0 GPa [42]. Our own calculations using PBE give a similar transition pressure of 0.5 GPa, and we also perform HSE calculations [43, 44] which increase the transition pressure to 2.5 GPa, in better agreement with experiment. Due to the computational cost of HSE calculations, we perform the finite temperature calculations using the PBE functional instead, and we expect that our results will be qualitatively correct. Figure 3 shows that, with increasing temperature and for pressures above 0.5 GPa, a band inversion occurs, inducing a transition from a topological to a normal phase. Experimental observation of a temperatureinduced topological phase transition should be simplest at pressures just above the zero-temperature transition pressure. More generally, temperature-induced topological phase transitions should be observable near critical values of other external parameters driving a topological phase transition. The pressure-temperature phase diagrams of Bi₂Te₃, Bi₂Se₃, and Sb₂Te₃ are qualitatively similar to that of Sb_2Se_3 . These materials, however, are deep inside the topological part of the phase diagram at ambient pressure so that unrealistically high temperatures would be needed to induce a transition to the normal state (see Fig. 1).

Our results show that in the Bi_2Se_3 family of compounds, increasing temperature favors the normal phase. This is at odds with the theoretical prediction of Refs. [15, 16], where it was argued that higher temperature should favor topological phases. The focus there is on electron-phonon coupling only, but we have shown that thermal expansion is equally important. Even if only electron-phonon coupling is considered, our calculations still show that temperature does not favor topological phases in the Bi₂Se₃ family of compounds. To understand the discrepancy, we note several possibilities. First, the analysis of Refs. [15, 16] only includes the socalled Fan term, which arises from treating the first-order phonon-induced change in the Hamiltonian at second order in perturbation theory. However, the Debye-Waller term, which arises from the second-order change in the Hamiltonian treated at first order in perturbation theory, has been shown to be equally important for the calculation of the temperature dependence of band gaps [21]. Our finite displacement approach includes both terms. Second, the analysis of Refs. [15, 16] assumes that the two bands that participate in the band inversion are well separated in energy from the rest of the bands. This ensures that, for sufficiently small gaps, the dominant contribution comes from intraband transitions, which have a gap-opening tendency in topological insulators. In the systems we have studied, the bands at Γ involved in the band inversion are not well separated in energy from other bands. For example, the conduction band minimum of Bi_2Te_3 and Sb_2Te_3 is not even at Γ , where band inversion occurs. Therefore, we do not expect that the analysis of Refs. [15, 16] applies in our case. Nonetheless, there is no reason why temperature could not favor topological order in some other materials that obey the assumptions laid out in Refs. [15, 16], and it would certainly be interesting to identify some such examples.

In summary, we have shown that thermal expansion and electron-phonon coupling drive the temperature dependence of the band structure of topological insulators. Increasing temperature favors the normal state in the Bi_2Se_3 family of compounds, and induces a topological phase transition in pressurized Sb_2Se_3 . Temperatureinduced changes to the band gaps reach 0.3 eV at 600 K, and are of similar size to the changes induced by electron correlation in these materials. Open questions remain, such as the effects of thermally induced changes in electron occupation, and the possible importance of nonadiabatic phenomena, especially close to band inversions.

Our work shows that first-principles calculations of the effects of temperature on topological materials are feasible, and that temperature can have important effects on the band structure and topological order of these materials. It should facilitate future work, for example in the search for a room temperature Chern insulator.

This work was funded by NSF grant DMR-1408838. B.M. thanks Robinson College, Cambridge, and the Cambridge Philosophical Society for a Henslow Research Fellowship.

* monserrat@physics.rutgers.edu

- D. Hsieh, D. Qian, L. Wray, Y. Xia, Y. S. Hor, R. J. Cava, and M. Z. Hasan, "A topological Dirac insulator in a quantum spin Hall phase," Nature 452, 970 (2008).
- [2] Xiaoxiang Xi, Chunli Ma, Zhenxian Liu, Zhiqiang Chen, Wei Ku, H. Berger, C. Martin, D. B. Tanner, and G. L. Carr, "Signatures of a pressure-induced topological quantum phase transition in BiTeI," Phys. Rev. Lett. 111, 155701 (2013).
- [3] Achintya Bera, Koushik Pal, D. V. S. Muthu, Somaditya Sen, Prasenjit Guptasarma, U. V. Waghmare, and A. K. Sood, "Sharp Raman anomalies and broken adiabaticity at a pressure induced transition from band to topological insulator in Sb₂Se₃," Phys. Rev. Lett. **110**, 107401 (2013).
- [4] Y. Liu, Y. Y. Li, S. Rajput, D. Gilks, L. Lari, P. L. Galindo, M. Weinert, V. K. Lazarov, and L. Li, "Tuning Dirac states by strain in the topological insulator Bi₂Se₃," Nat. Phys. **10**, 294 (2014).
- [5] Shi Liu, Youngkuk Kim, Liang Z. Tan, and Andrew M. Rappe, "Strain-induced ferroelectric topological insulator," Nano Lett. 16, 1663 (2016).
- [6] Minsung Kim, Choong H. Kim, Heung-Sik Kim, and Jisoon Ihm, "Topological quantum phase transitions driven by external electric fields in Sb₂Te₃ thin films," Proc. Natl. Acad. Sci. USA **109**, 671 (2012).
- [7] Tong Zhang, Jeonghoon Ha, Niv Levy, Young Kuk, and Joseph Stroscio, "Electric-field tuning of the surface band structure of topological insulator Sb₂Te₃ thin films," Phys. Rev. Lett. **111**, 056803 (2013).
- [8] Qihang Liu, Xiuwen Zhang, L. B. Abdalla, Adalberto Fazzio, and Alex Zunger, "Switching a normal insulator into a topological insulator via electric field with application to phosphorene," Nano Lett. 15, 1222 (2015).
- [9] Cui-Zu Chang, Jinsong Zhang, Xiao Feng, Jie Shen, Zuocheng Zhang, Minghua Guo, Kang Li, Yunbo Ou, Pang Wei, Li-Li Wang, Zhong-Qing Ji, Yang Feng, Shuaihua Ji, Xi Chen, Jinfeng Jia, Xi Dai, Zhong Fang, Shou-Cheng Zhang, Ke He, Yayu Wang, Li Lu, Xu-Cun Ma, and Qi-Kun Xue, "Experimental observation of the quantum anomalous Hall effect in a magnetic topological insulator," Science **340**, 167 (2013).
- [10] Kush Saha, Katherine Légaré, and Ion Garate, "Detecting band inversions by measuring the environment: Fingerprints of electronic band topology in bulk phonon linewidths," Phys. Rev. Lett. **115**, 176405 (2015).
- [11] O. Viyuela, A. Rivas, and M. A. Martin-Delgado, "Uhlmann phase as a topological measure for onedimensional fermion systems," Phys. Rev. Lett. 112, 130401 (2014).
- [12] Zhoushen Huang and Daniel P. Arovas, "Topological indices for open and thermal systems via Uhlmann's phase," Phys. Rev. Lett. 113, 076407 (2014).
- [13] O. Viyuela, A. Rivas, and M. A. Martin-Delgado, "Twodimensional density-matrix topological fermionic phases: Topological Uhlmann numbers," Phys. Rev. Lett. 113, 076408 (2014).

- [14] Jan Carl Budich and Sebastian Diehl, "Topology of density matrices," Phys. Rev. B 91, 165140 (2015).
- [15] Ion Garate, "Phonon-induced topological transitions and crossovers in Dirac materials," Phys. Rev. Lett. 110, 046402 (2013).
- [16] Kush Saha and Ion Garate, "Phonon-induced topological insulation," Phys. Rev. B 89, 205103 (2014).
- [17] Haijun Zhang, Chao-Xing Liu, Xiao-Liang Qi, Xi Dai, Zhong Fang, and Shou-Cheng Zhang, "Topological insulators in Bi₂Se₃, Bi₂Te₃ and Sb₂Te₃ with a single Dirac cone on the surface," Nat. Phys. 5, 438 (2009).
- [18] Alexey A. Soluyanov, Dominik Gresch, Zhijun Wang, QuanSheng Wu, Matthias Troyer, Xi Dai, and B. Andrei Bernevig, "Type-ii weyl semimetals," Nature 527, 495 (2015).
- [19] P. B. Allen and V. Heine, "Theory of the temperature dependence of electronic band structures," J. Phys. C 9, 2305 (1976).
- [20] Feliciano Giustino, "Electron-phonon interactions from first principles," arxiv:1603.06965 (2016).
- [21] Feliciano Giustino, Steven G. Louie, and Marvin L. Cohen, "Electron-phonon renormalization of the direct band gap of diamond," Phys. Rev. Lett. 105, 265501 (2010).
- [22] Elena Cannuccia and Andrea Marini, "Effect of the quantum zero-point atomic motion on the optical and electronic properties of diamond and trans-polyacetylene," Phys. Rev. Lett. 107, 255501 (2011).
- [23] Christopher E. Patrick and Feliciano Giustino, "Quantum nuclear dynamics in the photophysics of diamondoids," Nat. Commun. 4, 2006 (2013).
- [24] Bartomeu Monserrat and R. J. Needs, "Comparing electron-phonon coupling strength in diamond, silicon, and silicon carbide: First-principles study," Phys. Rev. B 89, 214304 (2014).
- [25] S. Poncé, G. Antonius, P. Boulanger, E. Cannuccia, A. Marini, M. Côté, and X. Gonze, "Verification of first-principles codes: Comparison of total energies, phonon frequencies, electron-phonon coupling and zeropoint motion correction to the gap between ABINIT and QE/Yambo," Comput. Mater. Sci. 83, 341 (2014).
- [26] Jinggeng Zhao, Haozhe Liu, Lars Ehm, Dawei Dong, Zhiqiang Chen, and Genda Gu, "High-pressure phase transitions, amorphization, and crystallization behaviors in Bi₂Se₃," J. Phys. Condens. Matter **25**, 125602 (2013).
- [27] G. Kresse and J. Hafner, "Ab initio molecular dynamics for liquid metals," Phys. Rev. B 47, 558 (1993).
- [28] G. Kresse and J. Hafner, "Ab initio molecular-dynamics simulation of the liquid-metal-amorphous-semiconductor transition in germanium," Phys. Rev. B 49, 14251 (1994).
- [29] G. Kresse and J. Furthmüller, "Efficiency of ab-initio total energy calculations for metals and semiconductors using a plane-wave basis set," Comput. Mater. Sci. 6, 15

(1996).

- [30] G. Kresse and J. Furthmüller, "Efficient iterative schemes for *ab initio* total-energy calculations using a plane-wave basis set," Phys. Rev. B 54, 11169 (1996).
- [31] John P. Perdew, Kieron Burke, and Matthias Ernzerhof, "Generalized gradient approximation made simple," Phys. Rev. Lett. 77, 3865 (1996).
- [32] P. E. Blöchl, "Projector augmented-wave method," Phys. Rev. B 50, 17953 (1994).
- [33] G. Kresse and D. Joubert, "From ultrasoft pseudopotentials to the projector augmented-wave method," Phys. Rev. B 59, 1758 (1999).
- [34] X. Chen, H. D. Zhou, A. Kiswandhi, I. Miotkowski, Y. P. Chen, P. A. Sharma, A. L. Lima Sharma, M. A. Hekmaty, D. Smirnov, and Z. Jiang, "Thermal expansion coefficients of Bi₂Se₃ and Sb₂Te₃ crystals from 10 K to 270 K," Appl. Phys. Lett. **99**, 261912 (2011).
- [35] Bartomeu Monserrat, G. J. Conduit, and R. J. Needs, "Extracting semiconductor band gap zero-point corrections from experimental data," Phys. Rev. B 90, 184302 (2014).
- [36] J.O. Barnes, J.A. Rayne, and R.W. Ure, "Lattice expansion of Bi_2Te_3 from 4.2 K to 600 K," Phys. Lett. A 46, 317 (1974).
- [37] Jonathan H. Lloyd-Williams and Bartomeu Monserrat, "Lattice dynamics and electron-phonon coupling calculations using nondiagonal supercells," Phys. Rev. B 92, 184301 (2015).
- [38] Jinwoong Kim and Seung-Hoon Jhi, "Topological phase transitions in group IV-VI semiconductors by phonons," Phys. Rev. B 92, 125142 (2015).
- [39] Oleg V. Yazyev, Emmanouil Kioupakis, Joel E. Moore, and Steven G. Louie, "Quasiparticle effects in the bulk and surface-state bands of Bi₂Se₃ and Bi₂Te₃ topological insulators," Phys. Rev. B 85, 161101 (2012).
- [40] Irene Aguilera, Christoph Friedrich, Gustav Bihlmayer, and Stefan Blügel, "GW study of topological insulators Bi₂Se₃, Bi₂Te₃, and Sb₂Te₃: Beyond the perturbative one-shot approach," Phys. Rev. B 88, 045206 (2013).
- [41] J. Vidal, X. Zhang, L. Yu, J.-W. Luo, and A. Zunger, "False-positive and false-negative assignments of topological insulators in density functional theory and hybrids," Phys. Rev. B 84, 041109 (2011).
- [42] Wei Li, Xin-Yuan Wei, Jian-Xin Zhu, C. S. Ting, and Yan Chen, "Pressure-induced topological quantum phase transition in Sb₂Se₃," Phys. Rev. B 89, 035101 (2014).
- [43] J. Paier, M. Marsman, K. Hummer, G. Kresse, I. C. Gerber, and J. G. Ángyán, "Screened hybrid density functionals applied to solids," J. Chem. Phys. **124**, 154709 (2006).
- [44] J. Paier, M. Marsman, K. Hummer, G. Kresse, I. C. Gerber, and J. G. Ángyán, "Erratum: Screened hybrid density functionals applied to solids [J. Chem. Phys. 124, 154709 (2006)]," J. Chem. Phys. 125, 249901 (2006).